

VESPUCCI

Technical specification

		RESULT
Description:	Protected leather. Tone-on-tone through from top to bottom European cowhide aniline dyed	
Size:	Full hide (4,90-5,50 SqMt)	
Finishing:	Uniform semi-cover finish	
Thickness:	1.2-1.3 mm	
Light Fastness:	ISO 105-B02	≥8 blue scale
Flex:	ISO 5402	100.000 cycles, No cracks
Adesion to finish:	ISO 11644	≥11,2 N/Cm2, No cracks
Color Fastness to rubbing (WET):	ISO 11640	300 cycles, 4/5
Color Fastness to rubbing (ALKALINE PERSPIRATION):	ISO 11640	100 cycles, 4/5
Color Fastness to rubbing (SALT WATER SOLUTION - 40g/l)	ISO 11640	100 cycles, 4/5
Color Fastness to rubbing (GASOLINE)	ISO 11640	10 cycles, 4/5
Color Fastness to rubbing (SURFACE SANITIZER 70% ALCHOOL)	ISO 11640	30 cycles, 4/5
Veslic test 4x10 cycles (WINE)	ISO 26082	4/5 grey scale
Martindale test 12kPa after 200 cylces (WINE)	ISO 26082	4/5 grey scale
Tensile Strength	ISO 3376	119N 8,5N/mm2 48,70%
Tear Strength	ISO 3377-2	139,5 N
Determination of water resistance (Bally)	ISO 5403	>180min
Flammability:	UNI EN 1021-1 (BS 5852 part 1)	Complies
	IMO MED B+D	Complies
Country of origin:	Italy	
Cleaning instruction		
Vespucci is protected from the most common domestic stains, which can be removed by dabbing the leather with a dry cloth, without rubbing.		
Wash with a damp sponge and a small amount of neutral soap, then pass a sponge dampened with water over the leather and dry with a cloth.		
Stain removers and detergents sold for treating fabrics must not be used, and it is important that leather articles are not exposed at length to direct sunlight.		
Slight difference in color between one batch and another are to be considered entirely normal		